# Technical Data Sheet







## THE TRANSPARENT MATERIAL

# VITRA DL375 is a photosensitive material for DWS stereolithography 3D printers, developed for high definition clear prototypes, liquid flow visualization and lighting. It does not turn yellow.

### HINTS FOR THE DESIGN

VITRA DL375 is suitable both for thin and thick models. It is the ideal material to obtain smooth and precise transparent models.

### THE VITRA SERIES

# The Vitra series includes all the materials suitable for the production of transparents prototypes and clear functional parts. These materials are extremely accurate and precise and were developed in-house by DWS.

### **FEATURES**

- Smooth Surfaces
- Transparent
- Not yellowing
- High Resolution and Precision
- High Accuracy

# TECHNICAL FEATURES OF THE LIQUID MATERIAL

Environmental Values for Use	22°C - 27°C - max, RH 40% - 60%
Appearance / Colour	Liquid / Transparent
Viscosity	1000 ~ 1400 mPa•s at 25°C
Density	1,01 g/cm <sup>3</sup>

# TECHNICAL CHARACTERISTICS OF THE RESIN AFTER UV CURING

Elongation at Break (%)	6 ~ 10
Tensile Strength (MPa)	45 ~ 55
Tensile Modulus (MPa)	1700 ~ 2200
Flexural Strenght (MPa)	80 ~ 105
Flexural Modulus (MPa)	2000 ~ 2500
HDT@1,81 MPa	42 ~ 47
Application / Use	Transparent Prototypes, Clear Functional Parts

Technical specification subject to change without notice.

### DWS srl

